



This listing of claims will replace all prior versions, and listings, of claims in the application:

Listing of Claims:

1. (Original) Liquid-crystalline medium based on a mixture of polar compounds having negative dielectric anisotropy, characterised in that it comprises at least one compound of the formula I



in which

R^0 and R^1 each, independently of one another, denote H, an alkyl or alkenyl radical having up to 15 C atoms which is unsubstituted, monosubstituted by CN or CF_3 or at least monosubstituted by halogen, where, in addition, one or more CH_2 groups in these radicals may be replaced by -O-, -S-, , - $C \equiv C$ -, -OC-O- or -O-CO- in such a way that O atoms are not linked directly to one another,





- A^1
- a) denotes a 1,4-cyclohexenylene or 1,4-cyclohexylene radical, in which one or two non-adjacent CH_2 groups may be replaced by -O- or -S-,
 - b) denotes a 1,4-phenylene radical, in which one or two CH groups may be replaced by N,
 - c) denotes a radical from the group consisting of piperidine-1,4-diyl-, 1,4-bicyclo[2.2.2]octylene-, naphthalene-2,6-diyl, decahydronaphthalene-2,6-diyl, 1,2,3,4-tetrahydro-naphthalene-2,6-diyl, phenanthrene-2,7-diyl and fluorene-2,7-diyl,


where the radicals a), b) and c) may be mono- or polysubstituted by halogen atoms,

Z^1 denotes $-\text{CO}-\text{O}-$, $-\text{O}-\text{CO}-$, $-\text{CF}_2\text{O}-$, $-\text{OCF}_2-$, $-\text{CH}_2\text{O}-$, $-\text{OCH}_2-$, $-\text{CH}_2\text{CH}_2-$, $-(\text{CH}_2)_4-$, $-\text{C}_2\text{F}_4-$, $-\text{CH}_2\text{CF}_2-$, $-\text{CF}_2\text{CH}_2-$, $-\text{CF}=\text{CF}-$, $-\text{CH}=\text{CF}-$, $-\text{CF}=\text{CH}-$, $-\text{CH}=\text{CH}-$, $-\text{C}\equiv\text{C}-$ or a single bond, and


m denotes 0, 1 or 2.

2. (Original) Liquid-crystalline medium according to Claim 1, characterised in that it comprises at least one compound selected from the formulae I1 to I18







I5




I6




I7




I8




I9




I10




I11




I12




I13




I14




I15



I16



I17





I18

in which

R^0 and R^1 have the meanings indicated in Claim 1.

3. (Currently Amended) Liquid-crystalline medium according to Claim 1 ~~or 2~~, characterised in that R^0 denotes H.
4. (Currently Amended) Liquid-crystalline medium according to Claim 2 ~~or 3~~, characterised in that it comprises at least one compound of the formula II.
5. (Currently Amended) Liquid-crystalline medium according to claim 1 ~~one of Claims 1 to 4~~, characterised in that it additionally comprises one or more compounds of the formulae IIA and/or IIB:




in which

R^2 denotes an alkyl or alkenyl radical having up to 15 C atoms which is unsubstituted, monosubstituted by CN or CF_3 or at least monosubstituted by halogen, where, in addition, one or more CH_2 groups in these radicals may each be replaced, independently of one another, by $-O-$, $-S-$, , $-C\equiv C-$, $-CO-$, $-CO-O-$, $-O-CO-$ or $-O-CO-O-$ in such a way that O atoms are not linked directly to one another,

p denotes 1 or 2, and


v denotes 1 to 6.

6. (Currently Amended) Liquid-crystalline medium according to claim 1 ~~one of Claims 1 to 5~~, characterised in that it additionally comprises one or more compounds of the formula III



in which

R^{31} and R^{32} each, independently of one another, denote a straight-chain alkyl, alkenyl, alkylalkoxy or alkoxy radical having up to 12 C atoms, and



7. (Currently Amended) Liquid-crystalline medium according to claim 1 ~~one of Claims 1 to 6~~, characterised in that it comprises one, two, three, four or more compounds of the formula I.
8. (Currently Amended) Liquid-crystalline medium according to claim 1 ~~one of Claims 1 to 7~~, characterised in that the proportion of compounds of the formula I in the mixture as a whole is at least 5% by weight.
9. (Currently Amended) Liquid-crystalline medium according to claim 1 ~~one of Claims 1 to 8~~, characterised in that the proportion of compounds of the formulae IIA and/or IIB in the mixture as a whole is at least 20% by weight.
10. (Currently Amended) Liquid-crystalline medium according to claim 1 ~~one of Claims 1 to 9~~, characterised in that the proportion of compounds of the formula III in the mixture as a whole is at least 5% by weight.
11. (Currently Amended) Liquid-crystalline medium according to claim 1 ~~one of Claims 1 to 10~~, characterised in that it essentially consists of

5-30 % by weight of one or more compounds of the formula I

and

20-70 % by weight of one or more compounds of the formulae IIA and/or IIB.

12. (Currently Amended) Electro-optical display with active-matrix addressing based on the ECB, PALC or IPS effect, characterised in that it contains, as dielectric, a liquid-crystalline medium according to claim 1 ~~one of Claims 1 to 11~~.